



# 2015 NATIONAL STAIN RANKING

## Solid Color Stain Two-Year Exposure Results

	Substrate	Resistance						Color Retain	General Appearance	Average Score
		Crack	Erosion	Flake	Mildew	Dirt	Water Spotting			
Motor City SolarMax	ACQ	8	8	10	10	9	10	8	8	9.05
Motor City SolarMax	Cedar	10	10	10	9	9	10	8	9	
Motor City SolarMax	Timbertech	8	8	10	10	9	10	8	8	
Flood SWF Solid	ACQ	9	8	10	10	7	9	8	7	8.84
Flood SWF Solid	Cedar	10	10	10	9	9	10	8	9	
Flood SWF Solid	Timbertech	8	7	10	10	8	10	9	7	
S-W Decksapes	ACQ	9	8	10	10	9	10	9	9	8.84
S-W Decksapes	Cedar	10	10	10	9	8	10	8	8	
S-W Decksapes	Timbertech	8	6	10	10	8	10	7	6	
Sears Weatherbeater	ACQ	8	8	10	10	9	10	9	8	8.75
Sears Weatherbeater	Cedar	10	9	10	9	8	9	7	7	
Sears Weatherbeater	Timbertech	8	7	10	10	9	10	8	7	
O'Leary Dual Coat	ACQ	6	8	7	10	9	10	8	6	8.71
O'Leary Dual Coat	Cedar	9	9	10	9	8	9	5	6	
O'Leary Dual Coat	Timbertech	8	7	10	10	9	10	8	7	
Sikkens Rubbol	ACQ	7	8	10	10	9	10	9	8	8.42
Sikkens Rubbol	Cedar	10	8	10	9	8	9	2	3	
Sikkens Rubbol	Timbertech	8	8	10	10	9	10	9	8	
Olympic Maximum	ACQ	7	8	10	10	8	10	9	8	8.42
Olympic Maximum	Cedar	10	8	10	9	8	10	4	3	
Olympic Maximum	Timbertech	8	7	10	10	9	10	9	7	
Behr Solid Deck Fence & Siding	ACQ	7	8	9	10	9	10	9	7	8.25
Behr Solid Deck Fence & Siding	Cedar	9	8	10	9	8	8	3	3	
Behr Solid Deck Fence & Siding	Timbertech	8	7	10	10	9	10	9	8	
Thompson WaterSeal Deck & House	ACQ	9	8	10	10	9	10	7	8	8.17
Thompson WaterSeal Deck & House	Cedar	10	8	10	9	7	8	5	4	
Thompson WaterSeal Deck & House	Timbertech	8	5	10	10	8	10	8	5	
Olympic Wood Protector	ACQ	9	8	10	10	9	10	7	8	8.13
Olympic Wood Protector	Cedar	9	9	10	9	8	10	2	2	
Olympic Wood Protector	Timbertech	8	6	10	10	8	10	7	6	
Ben Moore Arborcoat	ACQ	9	8	10	10	9	10	6	7	7.80
Ben Moore Arborcoat	Cedar	10	8	10	9	8	7	2	2	
Ben Moore Arborcoat	Timbertech	8	6	10	10	8	10	5	5	



Corresponding to ratings for each property tested ( 10 = Excellent, 0 = Poor )

\* TESTING WAS PERFORMED BY AN INDEPENDENT ACCREDITED TESTING LABORATORY IN 2015